

Product Data Sheets

Trubloc Concrete Products

Carew Airfield, Tenby, Pembrokeshire SA708SX

01646 654 531

All information is based on blocks made to Building Standards 6073: Part 1: 1981 & 1985

Product	Foundation Blocks
Properties/ Technical Data	(4")
Block Thickness	100mm
Average Compressive Strength	7N
Average Delivered Block Weight	20KG
Thermal Conductivity (K/Lambda)	1.12 W/mK
Thermal Resistance (R) a 3% M/C	0.09 m K/W
Dimensional Tolerances of Blocks	Part 1 1981 & 1985
Length Allowance	+/- 5mm
Height Allowance	+/- 3mm
Thickness Allowance	+/- 4 mm
Dry Shrinkage	0.025% - 0.05%